

**Pullulan-based nanoparticles: future therapeutic applications in transmucosal
protein delivery**

Susana Rodrigues, Ana Grenha*

CBME – Centre for Molecular and Structural Biomedicine / IBB – Institute for
Biotechnology and Bioengineering, 8005-139 Faro, Portugal

*Corresponding author:

University of Algarve

CBME/IBB, Faculty of Sciences and Technology

Campus de Gambelas

8005-139 Faro, Portugal

Tel.: +351 289800100 – Ext. 7441

Fax: +351 289818419

E-mail address: amgrenha@ualg.pt

Key-words: pullulan, nanoparticles, proteins, transmucosal delivery

Current advances in the field of drug delivery are aimed at finding adequate strategies for the administration of different drugs. Transmucosal delivery is the first-line option for the systemic delivery of many drugs, including proteins, a group of molecules with recognised therapeutic potential and wide range of applications (drug and genetic therapy, immunisation, among others). This strategy, however, demands developing adequate carriers, as proteins are very sensitive molecules, easily undergoing degradation in physiological media, mainly due to pH and enzymatic occurrences. Polymeric nanoparticles have taken the forefront of this carrier-design challenge, offering appealing properties that include a reduced size providing intimate contact with mucosal surfaces, which potentiates any active action of the carrier regarding transmucosal delivery. Nanoparticles have been generally demonstrated to improve protein pharmacokinetic profile, not only by providing increased stabilisation but, in some cases, also permitting controlled release and enhancing drug absorption [1]. Moreover, the high surface-to-volume ratio displayed by these carriers increases drug loading capacity [2]. Polysaccharides have been indicated for many years as the most promising materials in drug carrier development, namely regarding nanoparticles. In this regard, a particular emphasis is placed on chitosan. Other polysaccharides, however, have been paving their way, also showing great ability for protein delivery. Pullulan is one of those polysaccharides; the first works reporting the application of pullulan-based nanoparticles for drug delivery dating back to 1998, when a cholesteryl group-bearing pullulan was used to produce nanoparticles for the delivery of both an oncoprotein [3] and insulin [4].

Pullulan is a neutral, water soluble polysaccharide produced from starch by the fungus *Aureobasidium pullulans*, by means of a process of fermentation [5]. Chemically, this polymer consists of α -(1,6)-linked maltotriose residues, which in turn are composed of three glucose molecules connected to each other by α -(1,4) glycosidic bonds [6,7]. Several properties have been reported for this material that make it attractive for drug delivery purposes, including its adhesive ability, as well as the capacity to form fibers

and thin biodegradable films [7]. The high content of hydroxyl groups on pullulan chains further endows the polymer with inherent physiological activity and also provides chemical flexibility.

Biodegradability is a mandatory characteristic of any material being considered for an application in drug delivery, and pullulan is expected to comply with it. Actually, once administered it will be exposed to the hydrolysis of glycoside bonds and the subsequent metabolism of glucose [8]. The ability to adhere to cell surfaces might also be advantageous within the application, improving the carriers' residence time and, consequently, the potential for timely absorption of the encapsulated protein. In this regard, apart from the demonstrated role of pullulan on the adhesion of *Aureobasidium pullulans* to biological surfaces, such as leaves [9], cell adhesion to pullulan-based surfaces was reported in a number of occasions [10-12]. Pullulan-based nanoparticles were actually shown to adhere to the nasal epithelium in a study regarding nasal vaccination [13] and our group has also verified the adherence of pullulan nanoparticles to respiratory epithelial cells (Calu-3 and A549), although to a limited extent (unpublished data).

Pullulan has been increasingly described as matrix forming material of drug and gene nanocarriers [5,7,13-17]. The most common characteristic of these carriers is the use of hydrophobic derivatives of pullulan, namely cholesteryl-pullulan, because this provides an amphiphilic polymer with the capacity to form nanoparticles by self-aggregation. These nanoparticles have been demonstrated to form stable complexes with both hydrophobic and hydrophilic drugs, such as proteins, reinforcing their flexibility. In a remarkable detail, apart from the capacity to form nanocarriers with suitable properties for transmucosal protein delivery, it has also been shown that pullulan-based nanoparticles are able to preserve the structure of encapsulated proteins, thus ensuring their biological activity [4]. Nevertheless, although the potential application in protein delivery was mentioned frequently, the demonstration of results in the area has been scarce. The delivery of insulin, bovine serum albumin, DNA and IL-

12 was effectively proposed [4,15-18]. Our group has recently given a contribution to the field. Instead of using a hydrophobic derivative of pullulan, our strategy involved the synthesis of charged hydrophilic derivatives of the polymer that provided the possibility of establishing electrostatic interactions among them or with other charged materials of interest. From the synthesised derivatives (carboxylated, phosphorylated, aminated and sulphated) the latter two were used to produce polysaccharide-based nanoparticles, upon complexation with either chitosan or carrageenan, or even with each other. The carriers were produced using a mild technique of polyelectrolyte complexation, which only involves hydrophilic conditions and a simple mixture of solutions, while permitting a very rapid formation of the carriers (less than 10 minutes). These nanoparticles exhibited great ability for the association of proteins with distinct properties (insulin and BSA, molecular weight of 5.7 and 67 kDa, respectively) and were proposed for nasal and pulmonary transmucosal delivery. Having demonstrated a clear non-cytotoxic behaviour in model respiratory cell lines (Calu-3 and A549) [17], the nanoparticles also revealed to not induce an inflammatory response upon contact with the same cell lines (unpublished data). Finally, preliminary *in vivo* tests in rats demonstrated an increased therapeutic response of insulin-loaded pullulan-based nanoparticles administered intranasally as compared with an insulin solution of similar dose (unpublished data).

The analysis of all the data available on the literature suggests the adequacy of the biomaterial pullulan for drug delivery strategies. Particularly, although counting on a reduced number of works, pullulan-based nanoparticles reveal potential regarding transmucosal protein delivery. The ability to associate and release biomacromolecules is demonstrated, good indications are available concerning biocompatibility, and biodegradability is also ensured. However, the real possibilities of success should be considered on a rational and cautious basis. Looking at chitosan nanoparticles, for instance, which are incomparably more explored and for a longer time, after more than two decades of research and really good, diverse and important demonstrations of

effectiveness and safety, no formulation was made commercially available so far. Nanomedicine is still a controversial matter, mainly because of safety issues. The regulatory agencies demand uncountable studies and demonstrations to consider any approval, which is highly desirable if considering that global human health is the addressed subject. However, it is natural that nanomedicine, as a recent subject in the ambit of regulation, faces even more difficult challenges.

As a demonstration that nanomedicine is still in its infancy regarding the regulatory challenges to be faced, it is interesting to consider a work from 2012 that revealed the significant accumulation of nanoparticles (40 – 350 nm) in the ovaries [19]. When other organs like the lung, liver, spleen and kidneys are usually examined by everyone to determine the biodistribution of nanoparticles and, thus, evaluate potential toxicity, the ovaries seem to have been neglected. The observation of that work raises an extremely important question: although *in vitro* cell studies give very relevant indications on the biocompatibility behaviour of nanocarriers, it is becoming undeniable that a complete characterisation of potential toxicity is only possible with early *in vivo* studies. For this reason, keeping track of the whole biological portrait and the complex interactions between the nanocarrier and the biological structures, which might induce toxicological issues, is essential when designing a nanodelivery system.

It seems, then, that the potential of pullulan-based nanoparticles for transmucosal protein delivery is there, but a very long way is still ahead to cover.

Acknowledgements

This work was supported by national Portuguese funding through FCT - Fundação para a Ciência e a Tecnologia, project ref. PTDC/SAU-FCF/100291/2008, PTDC/DTP-FTO/0094/2012 and PEst-OE/EQB/LA0023/2013.

1. Grenha A. Chitosan nanoparticles: a survey of preparation methods. *Journal of Drug Targeting*, 20(4), 291-300 (2012).
2. de la Fuente M, Csaba N, Garcia-Fuentes M, Alonso MJ. Nanoparticles as protein and gene carriers to mucosal surfaces. *Nanomedicine*, 3, 845-857 (2008).
3. Gu X, Schmitt M, Hiasa A *et al.* A novel hydrophobized polysaccharide/oncoprotein complex vaccine induces in vitro and in vivo cellular and humoral immune responses against HER2-expressing murine sarcomas. *Cancer Research*, 58(15) (1998).
4. Akiyoshi K, Kobayashi S, Shichibe S *et al.* Self-assembled hydrogel nanoparticle of cholesterol-bearing pullulan as a carrier of protein drugs: Complexation and stabilization of insulin. *Journal of Controlled Release*, 54(3), 313-320 (1998).
5. Rekha M, Chandra P. Pullulan as a promising biomaterial for biomedical applications: A perspective. *Trends in Biomaterials and Artificial Organs*, 20(2), 000-000 (2007).
6. Mizrahy S, Peer D. Polysaccharides as building blocks for nanotherapeutics. *The Chemistry Society Reviews*, 41, 2623-2640 (2012).
7. Cheng K-C, Demirci A, Catchmark J. Pullulan: biosynthesis, production, and applications. *Applied Microbiology and Biotechnology*, 92(1), 29-44 (2011).
8. Teramoto N, Shibata M. Synthesis and properties of pullulan acetate. Thermal properties, biodegradability, and a semi-clear gel formation in organic solvents. *Carbohydrate Polymers*, 63(4), 476-481 (2006).
9. Pouliot JM, Walton I, Nolen-Parkhouse M, Abu-Lail LI, Camesano TA. Adhesion of *Aureobasidium pullulans* is controlled by uronic acid based polymers and pullulan. *Biomacromolecules*, 6(2), 1122-1131 (2005).
10. Shi L, Aid R, Le Visage C, Chew SY. Biomimicking polysaccharide nanofibers promote vascular phenotypes: A potential application for vascular tissue engineering. *Macromolecular Bioscience*, 12(3), 395-401 (2012).
11. Autissier A, Letourneur D, Le Visage C. Pullulan-based hydrogel for smooth muscle cell culture. *Journal of Biomedical Materials Research Part A*, 82A(2), 336-342 (2007).
12. Na K, Shin D, Yun K, Park K, KC L. Conjugation of heparin into carboxylated pullulan derivatives as an extracellular matrix for endothelial cell culture. *Biotechnology Letters*, 25(5), 381-385 (2003).
13. Nochi T, Yuki Y, Takahashi H *et al.* Nanogel antigenic protein-delivery system for adjuvant-free intranasal vaccines. *Nat Mater*, 9(7), 572-578 (2010).
14. Jeong Y-I, Nah J-W, Na H-K *et al.* Self-assembling nanospheres of hydrophobized pullulans in water. *Drug Development and Industrial Pharmacy*, 25(8), 917-927 (1999).
15. Gupta M, Gupta AK. Hydrogel pullulan nanoparticles encapsulating pBUDLacZ plasmid as an efficient gene delivery carrier. *Journal of Controlled Release*, 99(1), 157-166 (2004).
16. Shimizu T, Kishida T, Hasegawa U *et al.* Nanogel DDS enables sustained release of IL-12 for tumor immunotherapy. *Biochemical and Biophysical Research Communications*, 367(2), 330-335 (2008).
17. Dionísio M, Cordeiro C, Remuñán-López C, Seijo B, Rosa da Costa A, Grenha A. Pullulan-based nanoparticles as carriers for transmucosal protein delivery. *European Journal of Pharmaceutical Sciences*, 50, 102-113 (2013).
18. Ayame H, Morimoto N, Akiyoshi K. Self-assembled cationic nanogels for intracellular protein delivery. *Bioconjugate Chemistry*, 19(4), 882-890 (2008).
19. Schädlich A, Hoffmann S, Mueller T *et al.* Accumulation of nanocarriers in the ovary: A neglected toxicity risk? *Journal of Controlled Release*, 160(1), 105-112 (2012).