

# NON-LINEAR ANALYSIS OF PIEZOLAMINATED STRUCTURES

José Simões Moita<sup>\*</sup>, Cristóvão Mota Soares<sup>\*\*</sup>, and Carlos Mota Soares<sup>\*\*</sup>

<sup>\*</sup>Universidade do Algarve, Escola Superior de Tecnologia, Campus da Penha, 8000 Faro, Portugal

<sup>\*\*</sup> IDMEC-Instituto de Engenharia Mecânica-Instituto Superior Técnico, Av. Rovisco Pais, 1096-Lisboa Codex, Portugal.

## Introduction

In the recent years the study of smart structures has attracted significant researchers, due to their potential benefits in a wide range of applications, such as shape control, vibration suppression, noise attenuation and damage detection. The applications in aerospace industry are of great relevance, such as in active control of airplane wings, helicopter blade rotor, space antenna. The use of smart materials, such as piezoelectric materials, in the form of layers or patches embedded and/or surface bonded on laminated composite structures, can provide structures that combine the superior mechanical properties of composite materials and the capability to sense and adapt their static and dynamic response, becoming adaptive structures. The piezoelectric materials have the property of generate electrical charge under mechanical load or deformation, and the reverse, applying an electrical field to the material results in mechanical strain or stresses.

Many researchers considering mainly linear analysis have carried out the modeling of composite structures containing piezolaminated sensors and actuators using the finite element formulation. A pioneering work is due to Allik and Hughes (1970) which analyzed the interactions between electricity and elasticity by developing a tetrahedral element. Recent surveys can be found in Benjeddou (2000), Senthil *et al.* (1999) and Franco Correia *et al.* (2000). Recently Yi *et al.* (2000) has developed a 3D finite element model to carry out the non-linear dynamic response of structures with piezoelectric laminae.

In this paper we present a finite element model, based on classical plate theory, for static non-linear analysis of plate/shell structures with piezoelectric sensors and actuators. A simple and efficient three-node triangular fat plate element is used. The formulation introduces one electric potential degree of freedom for each piezoelectric layer of the finite element. To show the applicability of the proposed model two illustrative numerical examples are presented and compared with alternative solutions.

## Classical Plate Theory. Displacements and Strains.

The classical Kirchhoff plate theory is considered. The displacement field is given by:

$$u(x, y, z, t) = u_0 - z \frac{\partial w_0}{\partial x} \quad ; \quad v(x, y, z, t) = v_0 - z \frac{\partial w_0}{\partial y} \quad ; \quad w(x, y, z, t) = w_0 \quad (1)$$

where  $(u_0, v_0, w_0)$  are the displacements of the point on the reference plane of the laminate, and

$\theta_x = -\partial w / \partial y$  and  $\theta_y = \partial w / \partial x$  are the rotations about the Cartesian  $x$  and  $y$  axes respectively.

The present theory considers large displacements with small strains. The Green's strains components associated with displacement field of eq (1), are given (Reddy, 1999):

$$\begin{aligned}\epsilon_{xx} &= \frac{\partial u_0}{\partial x} - z \frac{\partial^2 w}{\partial x^2} + \frac{1}{2} \left[ \left( \frac{\partial u}{\partial x} \right)^2 + \left( \frac{\partial v}{\partial x} \right)^2 + \left( \frac{\partial w}{\partial x} \right)^2 \right] \\ \epsilon_{yy} &= \frac{\partial v_0}{\partial y} - z \frac{\partial^2 w}{\partial y^2} + \frac{1}{2} \left[ \left( \frac{\partial u}{\partial y} \right)^2 + \left( \frac{\partial v}{\partial y} \right)^2 + \left( \frac{\partial w}{\partial y} \right)^2 \right] \\ \gamma_{xy} &= \left( \frac{\partial u_0}{\partial y} + \frac{\partial v_0}{\partial x} \right) - z \left( 2 \frac{\partial^2 w}{\partial y \partial x} \right) + \left( \frac{\partial u}{\partial x} \frac{\partial u}{\partial y} + \frac{\partial v}{\partial x} \frac{\partial v}{\partial y} + \frac{\partial w}{\partial x} \frac{\partial w}{\partial y} \right)\end{aligned}\quad (2)$$

### Piezoelectric Laminates. Constitutive Equations

The piezoelectric constitutive equations, coupling mechanical and electrical fields, for a laminate, can be written as, Allik and Hughes (1970):

$$\begin{aligned}\bar{\mathbf{s}} &= \bar{\mathbf{Q}} \bar{\mathbf{e}} - \bar{\mathbf{e}} \bar{\mathbf{E}} \\ \bar{\mathbf{D}} &= \bar{\mathbf{e}}^T \bar{\mathbf{e}} + \bar{\mathbf{p}} \bar{\mathbf{E}}\end{aligned}\quad (3)$$

where  $\bar{\boldsymbol{\sigma}} = [\sigma_{xx} \ \sigma_{yy} \ \sigma_{xy}]^T$  is the elastic stress vector and  $\bar{\boldsymbol{\epsilon}} = [\epsilon_{xx} \ \epsilon_{yy} \ \gamma_{xy}]^T$  the elastic strain vector,  $\bar{\mathbf{Q}}$  the elastic constitutive matrix,  $\bar{\mathbf{e}}$  the piezoelectric stress coefficient matrix,  $\bar{\mathbf{E}}$  the electric field vector,  $\bar{\mathbf{D}}$  the electric displacement vector and  $\bar{\mathbf{p}}$  is the dielectric matrix. The electric field vector is the negative gradient of the electric potential, which is assumed to be applied and varying linearly in the thickness direction, i.e.

$$\bar{\mathbf{E}} = -\nabla \phi \quad (4)$$

$$\bar{\mathbf{E}} = \{0 \ 0 \ E_z\}^T \quad (5)$$

### Finite Element Formulation

The finite element used here is a three-node triangular flat plate element with six mechanical degrees of freedom per node, three displacements and three rotations of the displacement field of Kirchhoff theory, and one additional degree of freedom for each piezoelectric layer. The element local displacements are expressed in terms of nodal displacements through shape functions given in terms of area co-ordinates, hence:

$$\mathbf{d} = \sum_{i=1}^3 \mathbf{N}_i \mathbf{d}_i = \mathbf{N} \mathbf{a}^e ; \bar{\mathbf{e}}_m = \sum_{i=1}^3 \mathbf{B}_i^m \mathbf{d}_i = \mathbf{B}^m \mathbf{a}_m^e ; \bar{\mathbf{e}}_b = \sum_{i=1}^3 \mathbf{B}_i^b \mathbf{d}_i = \mathbf{B}^b \mathbf{a}_b^e ; \mathbf{E} = -\mathbf{B}^v \phi \quad (6)$$

For non-linear analysis, using an updated lagrangian formulation, Bathe (1982), we obtain:

$$\begin{aligned} & \sum_{K=1}^N \left\{ \int_{A^e} \int_{h_{k-1}}^{h_k} \delta \begin{Bmatrix} \mathbf{a} \\ \phi \end{Bmatrix}^T \begin{bmatrix} \mathbf{B}^{mb} & 0 \\ 0 & \mathbf{B}^v \end{bmatrix}^T \begin{bmatrix} \bar{\mathbf{Q}} & \bar{\mathbf{e}} \\ \bar{\mathbf{e}}^T & -\bar{\mathbf{p}} \end{bmatrix}_k \begin{bmatrix} \mathbf{B}^{mb} & 0 \\ 0 & \mathbf{B}^v \end{bmatrix} \begin{Bmatrix} \mathbf{a} \\ \phi \end{Bmatrix} dz \right\} {}^t dA^e + \\ & \left. \int_{A^e} \int_{h_{k-1}}^{h_k} \delta \begin{Bmatrix} \mathbf{a} \\ 0 \end{Bmatrix}^T \begin{bmatrix} \mathbf{B}^{nl} & 0 \\ 0 & 0 \end{bmatrix}^T \begin{Bmatrix} \bar{\boldsymbol{\sigma}} \\ 0 \end{Bmatrix}_k dz \right\} {}^t dA^e = \\ & {}^{t+\Delta t} \mathfrak{R}_t^e - \sum_{k=1}^N \int_{A^e} \int_{h_{k-1}}^{h_k} \delta \begin{Bmatrix} \mathbf{a} \\ \phi \end{Bmatrix}^T \begin{bmatrix} \mathbf{B}^{mb} & 0 \\ 0 & \mathbf{B}^v \end{bmatrix}^T \begin{Bmatrix} \bar{\boldsymbol{\sigma}} \\ \bar{\mathbf{D}} \end{Bmatrix}_k dz {}^t dA^e \quad (7) \end{aligned}$$

The equilibrium equations in non-linear analysis of laminated structures with piezoelectric actuators, using an updated lagrangian formulation, can be written as:

$${}^{t+\Delta t} \left( \left[ \mathbf{K}_{uu}^L + \mathbf{K}_{uu}^\sigma \right] \right)^{(k-1)} \{\Delta \mathbf{q}\}^{(k)} = {}^{t+\Delta t} \left\{ \mathbf{F}_{ext}^{mec} \right\} - {}^{t+\Delta t} \left\{ \mathbf{K}_{uv}^{L(A)} \Delta \mathbf{v}^{(A)} \right\} - \frac{{}^{t+\Delta t} \left\{ \mathbf{F}_{int} \right\}}{{}^{t+\Delta t}}$$

(8)

where  $\mathbf{F}^{act} = {}^{t+\Delta t} \left\{ \mathbf{K}_{uv}^{L(A)} \Delta \mathbf{v}^A \right\}$  is an additional force vector due to the electrical potential applied

to the actuators.

In case of piezoelectric sensors the equilibrium equations are:

$${}^{t+\Delta t} \left( \begin{bmatrix} \mathbf{K}_{uu}^L & \mathbf{K}_{uv}^{L(S)} \\ \mathbf{K}_{vu}^{L(S)} & \mathbf{K}_{vv}^{L(S)} \end{bmatrix} + \begin{bmatrix} \mathbf{K}_{uu}^\sigma & 0 \\ 0 & 0 \end{bmatrix} \right)^{(k-1)} \begin{Bmatrix} \Delta \mathbf{q} \\ \Delta \mathbf{v}^{(S)} \end{Bmatrix}^{(k)} = {}^{t+\Delta t} \left\{ \mathbf{F}_{ext} \right\} - \frac{{}^{t+\Delta t} \left\{ \mathbf{F}_{int} \right\}}{{}^{t+\Delta t}} \quad (9)$$

## Numerical Applications

### 1. Linear analysis of a piezoelectric bimorph beam.

A linear analysis of a cantilevered piezoelectric bimorph beam, with two PVDF layers bonded together and polarized in opposite directions, with the dimensions indicated in Figure 2, is considered. The mechanical and piezoelectric properties of the PVDF are:

$E_1 = E_2 = 2 \text{ GPa}$ ,  $G_{12} = 1 \text{ GPa}$ ,  $\nu_{12} = 0$ ,  $e_{31} = e_{32} = 0.046 \text{ C/m}^2$ ,  $p_{33} = 1.062 \times 10^{-10} \text{ F/m}$ . The top and bottom surfaces of the beam are subjected to an electric potential of 1V. The deflections in different locations of the beam, using a (5x2) element mesh, are presented in Table 1, which are compared with alternative solutions. The sensing voltage distribution of the bimorph beam for a prescribed tip deflection of 10 mm, is also analysed. The present predictions, and solutions obtained by other authors are shown in Table 2. The results are in good agreement with the alternative solutions.




Figure 2. Piezoelectric bimorph beam.

Location y (mm)	Deflections x 10 <sup>-7</sup> m				
	20	40	60	80	100
Analytical solution					
Suleman and Venkayya [12]	0.138	0.552	1.24	2.21	3.45
Q9-FSDT5P					
Franco <i>et al.</i> [4]	0.138	0.552	1.24	2.11	3.45
FSDT4P					
Suleman and Venkayya [12]	0.14	0.55	1.24	2.21	3.45
CPT					
Present Solution	0.137	0.550	1.240	2.210	3.45
Experimental					
Suleman and Venkayya [12]	-	-	-	-	3.45

Table 1. Deflections produced by a unit voltage.

Elements	Sensed voltage (V)				
	1 and 2	3 and 4	5 and 6	7 and 8	9 and 10
Q9-FSDT5P Franco <i>et al.</i> [4]	290	226	161	97	32
FSDT4P Suleman e Venkayya [12]	290	-	-	-	-
Present Solution (CPT)	295	229	163	98	32

Table 2. Sensed voltage distribution for a tip deflection of 10 mm.

## 2. Adaptive composite plate with surface bonded actuators

A simply-supported square plate (axa),  $a=0.1$  m, with two surface bonded piezoelectric layers PXE-52 is subjected to a uniform mechanical load of  $p_0=10$  kN/m<sup>2</sup>, and electrical potential of 151.35 V/-151.35 V. The lamination sequence of the plate is  $[p/45^\circ/-45^\circ/45^\circ/p]$ , where p represents the PXE-52 piezoelectric layers of thickness  $t=0.0002$  m, and the three inside layers are made from S-glass/epoxy, with thickness  $t=0.0004$  m. The properties of the PXE-52 are  $E_1 = E_2 = 62.5$  GPa,  $G_{12} = 24$  GPa,  $\nu_{12} = 0.3$ ,  $d_{31} = d_{32} = -280 \times 10^{-12}$  m/V,  $d_{33} = 700 \times 10^{-12}$  m/V,  $p_{33} = 3.45 \times 10^{-8}$  F/m, and for the S-glass/epoxy are  $E_1 = 55$  GPa,  $E_2 = 16$  GPa,  $G_{12} = 7.6$  GPa,  $\nu_{12} = 0.28$ . The results for different load cases, considering linear (L) and non-linear (NL) behavior of the plate, are presented in Figure 1.




Figure 1. Load-displacement curves for different load cases.

## Conclusions

The result obtained for mechanical load only ( $\mu=1.$ , in Figure 1), in linear analysis, was compared with Franco *et al.*, (1999), and an excellent agreement had been achieved. On other hand we observe that almost the same curves had been obtained for the cases of linear and non-linear analyses. The reason is because the range of mechanical and electrical loads is small.

## References

- Allik, H. e Hughes, T., (1970), "Finite Element Method for Piezoelectric Vibration", *Int. J. Num. Meth. Engng.*, 2, 151-157.
- Bathe, K. J., (1982) , "Finite Element Procedures in Engineering Analysis", Prentice-Hall Inc, Englewood Cliffs, New Jersey, USA.
- Benjeddou, A., (2000), "Advances in Piezoelectric Finite Element Modelling of Adaptive Structural Elements: A Survey", *Computer and Structures*, 76, 347-363.
- Franco Correia, V.M., Mota Soares, and C.M., Mota Soares, C.A., (1999), "Optimal Design of Composite Structures with Integrated Piezoelectric Laminæ", C.A. Mota Soares et al. (eds), *Mechanics of Composite Materials and Structures*, 389-408.
- Franco Correia, V.M., Aguiar Gomes, M.A., Suleman, A., Mota Soares, C.M., and Mota Soares, C.A., (2000), "Modelling and Design of Adaptive Composite Structures", *Comput. Methods Appl. Mech. Engrg.*, 185, 325-346.
- Senthil, V.G., Varadan, V.V., and Varadan, V.K., (1999), "A Review and critique of Theories for Piezoelectric Laminates", *Smart Material Structures*, 9, 24-28
- Reddy, J. N., (1997), "Mechanics of Laminated Composite Plates", CRC Press, Boca Raton, New York.
- Yi S., Ling, S.F., and Ying, M., (2000), " Large Deformations Finite Element Analyses of Composite Structures Integrated with Piezoelectric Sensors and Actuators", *Finite Elements in Analysis and Design*, 35, 1-15.